

ATTENTION: Ce tableau de compatibilité n'est qu'une indication. Merci de contacter votre revendeur pour obtenir de plus amples informations sur une utilisation de la pompe avec un type précis de liquide avant toute installation ou mise en service.

COMPATIBILITE AVEC PRODUITS CHIMIQUES

A = Pas d'effet - excellent
 B = Effet minimal - très bon
 C = Effet modéré - bon
 D = Effet passable - non toléré
 - = produit non testé

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Acetaldehyde5	B	C	A		A	A	A	-		A	A		A	A	A	-		B	-	A	A		B	C	-
Acetamide	-	-	B		-	A	-	-		B	-		-	B	-	-		-	-	-	-		-	-	-
Acetate Solvent2	D	B	B		-	A	A	-		B	A		-	B	A	-		D	-	A	-		D	B	-
Acetic Acid, Glacia1	B	B	B		A	A	A	-		B	A		A	B	A	-		B	-	A	-		B	B	D
Acetic Acid 20%	A	-	B		A	A	A	A		B	A		A	B	A	A		A	A	A	-		A	-	-
Acetic Acid 80%	B	-	B		-	A	A	A		B	A		-	B	A	A		B	A	A	-		B	-	-
Acetic Acid	A	B	B		A	A	A	B		B	A		A	B	A	B		A	B	A	-		A	B	D
Acetic Anhydride	A	A	A		A	A	A	D		A	A		A	A	A	D		A	D	A	A		A	A	-
Acetone6	B	C	A		A	A	A	D		A	A		A	A	A	D		B	D	A	-		B	C	A
Acetyl Chloride	-	-	C		A	A	A	-		C	A		A	C	A	-		-	-	A	-		-	-	-
Acetylene2	D	-	A		A	A	-	-		A	-		A	A	-	-		D	-	-	A		D	-	-
Acrylonitrile	B	-	A		A	C	-	-		A	-		A	A	-	-		B	-	-	-		B	-	C
Alcohol, Amyl	B	B	A		A	A	A	A		A	A		A	A	A	A		B	A	A	A		B	B	C

Tableau de compatibilité



Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Alcohol, Benzyl	A	D	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	D	-
Alcohol, Butyl	B	B	A		A	A	A	A		A	A		A	A	A	A		B	A	A	A		B	B	C
Alcohol, Diacetone2	D	-	A		-	A	-	-		A	-		-	A	-	-		D	-	-	A		D	-	-
Alcohol, Ethyl	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	B	B
Alcohol, Hexyl	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	-
Alcohol, Isobutyl	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	C		A	-	-
Alcohol, Isopropyl	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	C
Alcohol, Methyl6	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	B	A
Alcohol, Octyl	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	-
Alcohol, Propyl	A	-	A		-	A	A	B		A	A		-	A	A	B		A	B	A	C		A	-	-
Aluminum Chloride 20%	A	B	D		A	C	-	-		D	-		A	D	-	-		A	-	-	D		A	B	D
Aluminum Chloride	A	-	D		A	C	A	A		D	A		A	D	A	A		A	A	A	D		A	-	D
Aluminum Fluoride	A	B	D		-	C	A	A		D	A		-	D	A	A		A	A	A		A	B	-	
Aluminum Hydroxide6	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	-	D
Aluminum Potassium Sulfate (Alum), 10%	-	A	A		-	-	A	-		A	A		-	A	A	-		-	-	A	-		-	A	D
Aluminum Potassium Sulfate (Alum), 100%	A	B	D		-	A	A	-		D	A		-	D	A	-		A	-	A	-		A	B	-
Aluminum Sulfate	A	B	C		A	C	A	A		C	A		A	C	A	A		A	A	A	A		A	B	D
Amines	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-
Ammonia 10%	A	-	-		A	A	A	D		-	A		A	-	A	D		A	D	A	-		A	-	-

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Ammonia, Anhydrous	A	B	B		B	A	A	D		B	A		B	B	A	D		A	D	A	A		A	B	D
Ammonia, Liquids	A	D	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	D	-
Ammonia, Nitrate	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	-
Ammonium Bifluoride	A	-	C		-	A	-	-		C	-		-	C	-	-		A	-	-	A		A	-	-
Ammonium Carbonate	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	D		A	-	C
Ammonium Casenite	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Ammonium Chloride	A	B	A		A	C	A	A		A	A		A	A	A	A		A	A	A	A		A	B	D
Ammonium Hydroxide	A	B	A		A	A	A	-		A	A		A	A	A	-		A	-	A	A		A	B	-
Ammonium Nitrate	A	B	A		A	A	A	-		A	A		A	A	A	-		A	-	A	C		A	B	-
Ammonium Oxalate	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Ammonium Persulfate	A	-	A		-	A	A	D		A	A		-	A	A	D		A	D	A	C		A	-	D
Ammonium Phosphate,Dibasic	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	B	-
Ammonium Phosphate,Monobasic	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	B	-
Ammonium Phosphate,Tribasic	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	B	C
Ammonium Sulfate	A	B	D		A	B	A	A		D	A		A	D	A	A		A	A	A	A		A	B	C
Ammonium Thio-Sulfate	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	A		-	-	D
Amyl-Acetate	D	D	A		A	A	A	C		A	A		A	A	A	C		D	C	A	-		D	D	-
Amyl Alcohol	A	B	A		-	A	A	A		A	A		-	A	A	A		A	A	A	A		A	B	-
Amyl Chloride	D	D	C		-	B	A	A		C	A		-	C	A	A		D	A	A	-		D	D	-

Tableau de compatibilité



Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Aniline	B	C	A		A	A	A	C		A	A		A	A	A	C		B	C	A	-		B	C	-
Antifreeze	A	B	A		A	A	A	-		A	A		A	A	A	-		A	-	A	B		A	B	B
Antimony Trichloride	-	A	D		-	D	A	-		D	A		-	D	A	-		-	-	A	-		-	A	-
Aqua Regia (80%,HCL,20%,HNO)	C	D	D		-	D	A	C		D	A		-	D	A	C		C	C	A	D		C	D	-
Arochlor 1248	-	-	-		-	-	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Aromatic Hydrocarbons	-	C	-		-	A	-	-		-	-		-	-	-	-		-	-	-	A		-	C	-
Arsenic Acid	A	B	A		-	A	A	A		A	A		-	A	A	A		A	A	A	A		A	B	D
Asphalt	A	-	B		A	A	-	-		B	-		A	B	-	-		A	-	-	D		A	-	C
Barium Carbonate	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	B	-
Barium Chloride	A	B	D		A	A	A	A		D	A		A	D	A	A		A	A	A	A		A	B	-
Barium Cyanide	-	B	-		-	A	-	-		-	-		-	-	-	-		-	-	-	-		-	B	-
Barium Hydroxide	A	B	C		A	A	A	A		C	A		A	C	A	A		A	A	A	A		A	B	C
Barium Nitrate	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	D		-	-	-
Barium Sulfate	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	-		A	B	C
Barium Sulfide	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	B	C
Beer2	D	B	A		-	A	A	A		A	A		-	A	A	A		D	A	A	A		D	B	D
Beet Sugar Liquids	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	-	A
Benzaldehyde3	D	D	A		A	A	A	C		A	A		A	A	A	C		D	C	A	-		D	D	-
Benzene2	D	D	A		A	A	A	B		A	A		A	A	A	B		D	B	A	C		D	D	-

Tableau de compatibilité



Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Benzoic Acid2	D	B	A		-	A	A	A		A	A		-	A	A	A		D	A	A	C		D	B	D
Benzol	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	-	-
Borax (Sodium Borate)	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	D		A	B	-
Boric Acid	A	B	A		-	A	A	A		A	A		-	A	A	A		A	A	A	A		A	B	D
Brewery Slop	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	A		-	-	-
Bromine2 (wet)	D	D	D		D	D	A	A		D	A		D	D	A	A		D	A	A	D		D	D	D
Butadiene	-	-	A		B	A	A	A		A	A		B	A	A	A		-	A	A	-		-	-	C
Butane1 2	D	C	A		A	A	A	A		A	A		A	A	A	A		D	A	A	-		D	C	C
Butanol	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-
Butter	-	-	B		-	A	-	-		B	-		-	B	-	-		-	-	-	D		-	-	D
Buttermilk	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	D
Butylene	-	-	B		A	A	A	-		B	A		A	B	A	-		-	-	A	A		-	-	-
Butyl Acetate1	D	C	-		A	C	A	C		-	A		A	-	A	C		D	C	A	D		D	C	-
Butyric Acid1	A	-	B		-	A	A	A		B	A		-	B	A	A		A	A	A	A		A	-	D
Calcium Bisulfate	-	-	D		-	A	A	-		D	A		-	D	A	-		-	-	A	-		-	-	D
Calcium Bisulfide	A	B	-		-	B	A	-		-	A		-	-	A	-		A	-	A	-		A	B	-
Calcium Bisulfite	A	-	B		-	A	A	A		B	A		-	B	A	A		A	A	A	-		A	-	-
Calcium Carbonate	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	B	D
Calcium Chlorate	-	A	B		-	A	A	-		B	A		-	B	A	-		-	-	A	-		-	A	-

Tableau de compatibilité

PRESSOL

	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
Fluids	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Calcium Chloride	A	B	A		A	D	A	A		A	A		A	A	A	A		A	A	A	A		A	B	C
Calcium Hydroxide	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	B	-
Calcium Hypochlorite	A	B	D		-	C	A	A		D	A		-	D	A	A		A	A	A	A		A	B	D
Calcium Sulfate	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A			A	B	-
Calgon	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	D		A	-	D
Cane Juice ²	D	-	A		-	A	-	-		A	-		-	A	-	-		D	-	-	A		D	-	-
Carbolic Acid (See Phenol)																									
Carbon Bisulfide ²	D	-	A		-	A	-	-		A	-		-	A	-	-		D	-	-	-		D	-	-
Carbon Dioxide (wet)	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	C
Carbon Disulfide ²	D	D	B		A	A	A	-		B	A		A	B	A	-		D	-	A	-		D	D	-
Carbon Monoxide	A	B	A		-	A	-	-		A	-		-	A	-	-		A	-	-	-		A	B	-
Carbon Tetrachloride ^{1 2}	D	D	B		C	B	A	A		B	A		C	B	A	A		D	A	A	A		D	D	C
Carbonated Water	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	-		A	-	D
Carbonic Acid	A	B	A		-	B	A	A		A	A		-	A	A	A		A	A	A	A		A	B	D
Catsup	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	D		A	-	D
Chloroacetic Acid ²	D	D	D		-	D	A	D		D	A		-	D	A	D		D	D	A	-		D	D	D
Chloric Acid	-	-	D		-	D	A	-		D	A		-	D	A	-		-	-	A	D		-	-	-
Chlorinated Glue	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	D		-	-	D
Chlorine, Anhydrous Liquid	D	D	D		C	D	A	-		D	A		C	D	A	-		D	-	A	-		D	D	C
Chlorine (dry)	-	-	A		C	A	A	-		A	A		C	A	A	-		-	-	A	-		-	-	-

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Chlorine Water	D	-	-		C	D	A	A		-	A		C	-	A	A		D	A	A	-		D	-	D
Chlorobenzene (Mono)	D	D	A		A	A	A	A		A	A		A	A	A	A		D	A	A	-		D	D	-
Chloroform	D	D	A		C	A	A	C		A	A		C	A	A	C		D	C	A			D	D	D
Chlorosulfonic Acid1	D	D	D		D	-	A	D		D	A		D	D	A	D		D	D	A	-		D	D	-
Chlorox (Bleach)	D	-	A		C	A	A	-		A	A		C	A	A	-		D	-	A	D		D	-	D
Chocolate Syrup	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	D		A	-	D
Chromic Acid 5%	A	B	A		A	A	-	-		A	-		A	A	-	-		A	-	-	C		A	B	D
Chromic Acid 10%	A	-	B		-	-	A	A		B	A		-	B	A	A		A	A	A	-		A	-	-
Chromic Acid 30%	A	-	B		-	-	A	B		B	A		-	B	A	B		A	B	A	-		A	-	-
Chromic Acid 50%	B	C	B		B	B	A	C		B	A		B	B	A	C		B	C	A	C		B	C	D
Cider	-	B	A		-	A	-	-		A	-		-	A	-	-		-	-	-	D		-	B	D
Citric Acid	B	B	A		-	A	A	A		A	A		-	A	A	A		B	A	A	B		B	B	D
Citric Oils	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	-		A	-	-
Coffee	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	-	C
Copper Chloride	A	B	D		A	D	A	A		D	A		A	D	A	A		A	A	A	D		A	B	D
Copper Cyanide	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	B		A	B	D
Copper Fluoborate	-	A	D		-	D	A	-		D	A		-	D	A	-		-	-	A	B		-	A	D
Copper Nitrate	A	B	A		-	A	A	A		A	A		-	A	A	A		A	A	A	A		A	B	-
Copper Sulfate (5% Solution)	A	B	A		A	A	A	-		A	A		A	A	A	-		A	-	A	-		A	B	D

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Copper Sulfate	A	-	B		-	-	A	A		B	A		-	B	A	A		A	A	A	B		A	-	-
Cream	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	B		A	-	D
Cresols2	C	D	A		A	A	-	-		A	-		A	A	-	-		C	-	-	-		C	D	-
Cresylic Acid	-	C	A		-	A	A	B		A	A		-	A	A	B		-	B	A	-		-	C	-
Cyclohexane	D	-	A		A	-	-	-		A	-		A	A	-	-		D	-	-	-		D	-	-
Cyanic Acid	-	-	A		-	-	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Detergents	A	B	A		A	A	-	-		A	-		A	A	-	-		A	-	-	-		A	B	-
Dichlorethane	-	D	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	D	-
Diesel Fuel	D	-	A		A	A	-	-		A	-		A	A	-	-		D	-	-	-		D	-	A
Diethylamine	C	-	A		-	-	A	-		A	A		-	A	A	-		C	-	A	-		C	-	-
Diethylene Glycol	-	B	A		-	-	-	-		A	-		-	A	-	-		-	-	-	-		-	B	-
Diphenyl Oxide	-	-	A		-	-	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Dyes	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Epsom Salts (Magnesium Sulfate)	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	-
Ethane	-	-	A		-	-	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Ethanolamine	-	-	A		A	A	-	-		A	-		A	A	-	-		-	-	-	B		-	-	-
Ether3	-	-	A		A	A	-	-		A	-		A	A	-	-		-	-	-	-		-	-	-
Ethyl Acetate2	C	C	A		A	A	A	D		A	A		A	A	A	D		C	D	A	A		C	C	-
Ethyl Chloride	D	D	A		A	A	A	A		A	A		A	A	A	A		D	A	A	D		D	D	C

Tableau de compatibilité

PRESSOL

	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Ethyl Sulfate	-	-	D		-	-	-	-		D	-		-	D	-	-		-	-	-	-		-	-	-
Ethylene Chloride ²	D	-	A		A	A	A	-		A	A		A	A	A	-		D	-	A	-		D	-	C
Ethylene Dichloride	A	D	A		A	A	A	-		A	A		A	A	A	-		A	-	A	-		A	D	-
Ethylene Glycol ⁴	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	B		A	B	B
Ethylene Oxide	-	-	-		-	A	A	-		-	A		-	-	A	-		-	-	A	-		-	-	-
Fatty Acids	A	B	A		-	A	A	A		A	A		-	A	A	A		A	A	A	D		A	B	D
Ferric Chloride	A	B	D		A	D	A	A		D	A		A	D	A	A		A	A	A	B		A	B	D
Ferric Nitrate	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	-		A	B	-
Ferric Sulfate	A	-	A		A	C	A	A		A	A		A	A	A	A		A	A	A	-		A	-	D
Ferrous Chloride	A	B	D		A	D	A	A		D	A		A	D	A	A		A	A	A	A		A	B	D
Ferrous Sulfate	A	B	A		A	C	A	A		A	A		A	A	A	A		A	A	A	A		A	B	D
Fluoboric Acid	A	B	D		-	B	A	A		D	A		-	D	A	A		A	A	A	A		A	B	D
Fluorine	-	C	D		-	D	C	-		D	C		-	D	C	-		-	-	C	-		-	C	D
Fluosilicic Acid	A	B	-		-	B	A	A		-	A		-	-	A	A		A	A	A	-		A	B	D
Formaldehyde 40%	A	-	-		A	A	A	B		-	A		A	-	A	B		A	B	A	-		A	-	-
Formaldehyde	A	B	A		A	A	A	-		A	A		A	A	A	-		A	-	A	C		A	B	D
Formic Acid ⁶	A	B	A		A	B	A	A		A	A		A	A	A	A		A	A	A	B		A	B	D
Fruit Juice	A	B	A		-	A	D	-		A	D		-	A	D	-		A	-	D	-		A	B	D
Fuel Oils	B	D	A		A	A	A	A		A	A		A	A	A	A		B	A	A	-		B	D	C

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Furan Resin	-	-	A		A	A	A	-		A	A		A	A	A	-		-	-	A	A		-	-	A
Furfural1	D	D	A		A	A	A	D		A	A		A	A	A	D		D	D	A	A		D	D	-
Gallic Acid	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	D
Gasoline1 4	C	D	A		A	A	A	A		A	A		A	A	A	A		C	A	A	B		C	D	C
Gelatin	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	D		A	-	D
Glucose	A	B	-		-	A	A	-		-	A		-	-	A	-		A	-	A	A		A	B	-
Glue P.V.A.1	-	-	B		-	A	A	-		B	A		-	B	A	-		-	-	A	-		-	-	-
Glycerine	A	-	A		-	A	A	A		A	A		-	A	A	A		A	A	A	A		A	-	-
Glycolic Acid	A	B	-		A	-	-	-		-	-		A	-	-	-		A	-	-	-		A	B	-
Gold Monocyanide	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	A		-	-	D
Grape Juice	-	B	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	B	D
Grease4	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-
Heptane1	D	D	-		A	A	A	A		-	A		A	-	A	A		D	A	A	-		D	D	-
Hexane1	C	-	A		A	A	A	A		A	A		A	A	A	A		C	A	A	-		C	-	-
Honey	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	-		A	-	A
Hydraulic oils (Petroleum)1	D	-	A		-	A	A	-		A	A		-	A	A	-		D	-	A	-		D	-	-
Hydraulic Oils (Synthetic)1	D	-	A		-	A	-	-		A	-		-	A	-	-		D	-	-	-		D	-	A
Hydrazine	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	C
Hydrobromic Acid 20%	A	-	-		-	D	A	A		-	A		-	-	A	A		A	A	A	-		A	-	-

Tableau de compatibilité



	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Fluids																									
Hydrobromic Acid ⁴	B	B	D		-	D	A	A		D	A		-	D	A	A		B	A	A	D		B	B	D
Hydrochloric/Muratic Acid (Dry gas)	-	-	C		-	A	A	-		C	A		-	C	A	-		-	-	A	-		-	-	-
Hydrochloric/Muratic Acid (20%) ⁴	A	A	D		D	D	A	A		D	A		D	D	A	A		A	A	A	A		A	A	D
Hydrochloric/Muratic Acid (37%) ⁴	A	A	D		D	D	A	A		D	A		D	D	A	A		A	A	A	C		A	A	D
Hydrochloric/Muratic Acid (100%)	-	A	D		-	D	A	-		D	A		-	D	A	-		-	-	A	-		-	A	D
Hydrocyanic Acid	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	B	-
Hydrocyanic Acid (Gas 10%)	-	-	D		-	D	A	-		D	A		-	D	A	-		-	-	A	-		-	-	-
Hydrofluoric Acid (20%) ¹	A	C	D		C	D	A	-		D	A		C	D	A	-		A	-	A	D		A	C	D
Hydrofluoric Acid (75%) ^{1 2}	B	C	C		C	D	A	A		C	A		C	C	A	A		B	A	A	D		B	C	D
Hydrofluoric Acid 100%	-	D	B		C	B	A	-		B	A		C	B	A	-		-	-	A	-		-	D	D
Hydrofluosilicic Acid (20%)	A	-	D		-	D	A	-		D	A		-	D	A	-		A	-	A	D		A	-	D
Hydrofluosilicic Acid	-	-	D		-	D	A	-		D	A		-	D	A	-		-	-	A	-		-	-	-
Hydrogen Gas	-	-	A		-	A	A	A		A	A		-	A	A	A		-	A	A	-		-	-	-
Hydrogen Peroxide 10%	-	A	C		B	C	A	-		C	A		B	C	A	-		-	-	A	-		-	A	D
Hydrogen Peroxide 30%	A	-	-		C	B	A	-		-	A		C	-	A	-		A	-	A	-		A	-	-
Hydrogen Peroxide	A	B	A		C	B	A	C		A	A		C	A	A	C		A	C	A	D		A	B	D
Hydrogen Sulfide, Aqueous Solution	A	B	D		A	A	A	A		D	A		A	D	A	A		A	A	A	D		A	B	D
Hydrogen Sulfide (dry)	-	-	C		A	A	A	-		C	A		A	C	A	-		-	-	A	-		-	-	-

Tableau de compatibilité

PRESSOL

	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003	
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel	
Fluids																										
Hydroxyacetic Acid (70%)	-	-	-		-	-	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-	
Ink	-	B	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	B	D	
Iodine	D	D	D		-	D	A	-		D	A		-	D	A	-		D	-	A	-		D	D	D	
Iodine (In Alcohol)	B	-	-		-	B	A	-		-	A		-	-	A	-		B	-	A	-		B	-	-	
Iodoform	-	-	C		-	A	A	-		C	A		-	C	A	-		-	-	A	-		-	-	C	
Isotane2	D	-	-		-	-	-	-		-	-		-	-	-	-		D	-	-	-		D	-	-	
Isopropyl Acetate	-	-	-		-	B	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-	
Isopropyl Ether2	D	-	-		-	A	A	-		-	A		-	-	A	-		D	-	A	-		D	-	-	
Jet Fuel (JP#,JP4,JP5)	D	-	A		A	A	A	A		A	A		A	A	A	A		D	A	A	D		D	-	A	
Kerosene2	D	D	A		A	A	A	A		A	A		A	A	A	A		D	A	A	A		D	D	D	
Ketones	D	D	A		A	A	A	D		A	A		A	A	A	D		D	D	A	A		D	D	D	
Lacquers	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	C	
Lacquer Thinners	B	-	-		-	A	A	-		-	A		-	-	A	-		B	-	A	-		B	-	-	
Lactic Acid	A	B	A		A	B	A	C		A	A		A	A	A	C		A	C	A	-		A	B	D	
Lard	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	D		A	-	-	
Latex	-	B	A		-	A	-	-		A	-		-	A	-	-		-	-	-	D		-	B	-	
Lead Acetate	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	B	-	
Lead Sulfamate	A	-	-		-	-	-	-		-	-		-	-	-	-		A	-	-	-		A	-	-	
Ligroin3	D	-	-		-	A	-	-		-	-		-	-	-	-		D	-	-	-		D	-	-	

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Lime	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	D		-	-	-
Lubricants	A	-	A		A	A	A	-		A	A		A	A	A	-		A	-	A	A		A	-	-
Magnesium Carbonate	A	B	A		-	A	-	-		A	-		-	A	-	-		A	-	-	-		A	B	-
Magnesium Chloride	A	B	B		A	B	A	-		B	A		A	B	A	-		A	-	A	A		A	B	D
Magnesium Hydroxide	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	D		A	B	-
Magnesium Nitrate	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	B	-
Magnesium Oxide	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Magnesium Sulfate	A	B	B		A	A	A	-		B	A		A	B	A	-		A	-	A	A		A	B	C
Maleic Acid	C	-	A		-	A	A	-		A	A		-	A	A	-		C	-	A	-		C	-	-
Maleic Anhydride	-	-	-		-	-	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Malic Acid	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-
Mash	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Mayonnaise	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	-	D
Melamine	-	-	D		-	D	-	-		D	-		-	D	-	-		-	-	-	-		-	-	-
Mercuric Chloride (Dilute Solution)	A	B	D		-	D	A	-		D	A		-	D	A	-		A	-	A	A		A	B	D
Mercuric Cyanide	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A			A	B	-
Mercury	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	D		A	B	-
Methanol (See Alcohol Methyl)																									
Methyl Acetate	-	-	-		-	A	A	-		-	A		-	-	A	-		-	-	A	-		-	-	-

Tableau de compatibilité

PRESSOL

	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Methyl Acrylate	-	-	-		-	-	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Methyl Acetone	-	-	-		-	A	A	-		-	A		-	-	A	-		-	-	A	-		-	-	-
Methyl Alcohol 10%	-	-	-		-	A	A	-		-	A		-	-	A	-		-	-	A	-		-	-	-
Methyl Bromide	-	D	-		-	-	-	-		-	-		-	-	-	-		-	-	-	-		-	D	-
Methyl Butyl Ketone	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Methyl Cellosolve	A	-	-		-	-	-	-		-	-		-	-	-	-		A	-	-	-		A	-	-
Methyl Chloride	D	D	A		-	A	A	A		A	A		-	A	A	A		D	A	A	-		D	D	-
Methyl Dichloride	-	-	-		-	-	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Methyl Ethyl Ketone	A	D	A		A	A	A	D		A	A		A	A	A	D		A	D	A	A		A	D	-
Methyl Isobutyl Ketone2	C	-	-		A	A	A	D		-	A		A	-	A	D		C	D	A	-		C	-	-
Methyl Isopropyl Ketone	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Methyl Methacrylate	-	-	-		-	-	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Methylamine	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Methylene Chloride	B	D	B		A	B	A	D		B	A		A	B	A	D		B	D	A	-		B	D	-
Milk	A	B	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	B	D
Molasses	A	B	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	B	-
Mustard	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	D		A	-	C
Naphtha	A	D	A		A	A	A	A		A	A		A	A	A	A		A	A	A	A		A	D	-
Naphthalene	B	D	A		A	B	A	A		A	A		A	A	A	A		B	A	A	A		B	D	-

Tableau de compatibilité



Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Nickel Chloride	A	B	A		-	B	A	A		A	A		-	A	A	A		A	A	A	A		A	B	D
Nickel Sulfate	A	B	A		-	B	A	A		A	A		-	A	A	A		A	A	A	C		A	B	D
Nitric Acid (10% Solution)	A	B	A		D	A	A	A		A	A		D	A	A	A		A	A	A	-		A	B	D
Nitric Acid (20% Solution)	A	B	A		C	A	A	B		A	A		C	A	A	B		A	B	A	-		A	B	D
Nitric Acid (50% Solution)	D	C	A		C	A	A	B		A	A		C	A	A	B		D	B	A	-		D	C	D
Nitric Acid (Concentrated Solution)	D	D	D		C	B	A	-		D	A		C	D	A	-		D	-	A	-		D	D	D
Nitrobenzene2	C	D	A		B	B	A	D		A	A		B	A	A	D		C	D	A	-		C	D	-
Oil, Aniline	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	D		A	-	A
Oil, Anise	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Oil, Bay	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Oil, Bone	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Oil, Castor	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	B
Oil, Cinnamon	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	-	-
Oil, Citric	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	-		A	-	D
Oil, Clove	B	-	A		-	A	-	-		A	-		-	A	-	-		B	-	-	A		B	-	-
Oil, Coconut	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	B
Oil, Cod Liver	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	-
Oil, Corn	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	-		A	-	B
Oil, Cotton Seed	A	-	A		A	A	A	-		A	A		A	A	A	-		A	-	A	A		A	-	B

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Oil, Creosote2	D	-	A		-	A	-	-		A	-		-	A	-	-		D	-	-	-		D	-	-
Oil, Diesel Fuel (2D,3D,4D,5D)	A	-	A		A	A	-	-		A	-		A	A	-	-		A	-	-	-		A	-	-
Oil, Fuel (1,2,3,5A,5B,6)	B	-	A		-	A	A	-		A	A		-	A	A	-		B	-	A	-		B	-	-
Oil, Ginger	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	-
Oil, Hydraulic(See Hydraulic)																					-				
Oil, Lemon	D	-	A		-	A	-	-		A	-		-	A	-	-		D	-	-	A		D	-	-
Oil, Linseed	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	B
Oil, Mineral	B	-	A		A	A	-	-		A	-		A	A	-	-		B	-	-	A		B	-	B
Oil, Olive	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	-	B
Oil, Orange	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	-	-
Oil, Palm	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	-
Oil, Peanut3	D	-	A		-	A	-	-		A	-		-	A	-	-		D	-	-	A		D	-	B
Oil, Peppermint2	D	-	A		-	A	-	-		A	-		-	A	-	-		D	-	-	A		D	-	-
Oil, Pine	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	A		-	-	C
Oil, Rape Seed	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	-
Oil, Rosin	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	-
Oil, Sesame Seed	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	B
Oil, Silicone	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	-
Oil, Soybean	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	-	B
Oil, Sperm	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	-

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Oil, Tanning	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	-
Oil, Turbine	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	B
Oleic Acid	C	D	A		-	A	A	-		A	A		-	A	A	-		C	-	A	-		C	D	C
Oleum 25%	-	-	-		-	-	A	B		-	A		-	-	A	B		-	B	A	-		-	-	-
Oleum	D	-	-		-	A	A	D		-	A		-	-	A	D		D	D	A	-		D	-	-
Oxalic Acid (cold)	A	A	A		-	B	A	-		A	A		-	A	A	-		A	-	A	-		A	A	D
Paraffin	A	-	A		-	A	A	A		A	A		-	A	A	A		A	A	A	-		A	-	-
Pentane	-	-	C		-	C	A	-		C	A		-	C	A	-		-	-	A	-		-	-	-
Perchloroethylene2	D	-	A		A	A	A	A		A	A		A	A	A	A		D	A	A	D		D	-	-
Petrolatum	-	-	-		-	A	A	-		-	A		-	-	A	-		-	-	A	-		-	-	C
Phenol 10%	-	-	A		A	A	A	-		A	A		A	A	A	-		-	-	A	-		-	-	-
Phenol (Carbolic Acid)	B	D	A		A	A	A	A		A	A		A	A	A	A		B	A	A	D		B	D	D
Phosphoric Acid (40% Solution)	A	B	B		A	A	A	-		B	A		A	B	A	-		A	-	A	-		A	B	D
Phosphoric Acid (40% - 100% Solution)	A	C	C		A	B	A	-		C	A		A	C	A	-		A	-	A	-		A	C	D
Phosphoric Acid (Crude)	-	C	D		A	C	A	A		D	A		A	D	A	A		-	A	A	D		-	C	D
Phosphoric Anhydride (Dry or Moist)	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-
Phosphoric Anhydride (Molten)	-	D	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	D	-
Photographic (Developer)	A	B	C		-	A	-	-		C	-		-	C	-	-		A	-	-	A		A	B	D
Phthalic Anhydride	-	-	A		-	B	A	-		A	A		-	A	A	-		-	-	A	-		-	-	C

Tableau de compatibilité



Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003	
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel	
Picric Acid	-	A	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	A	D	
Plating Solutions																										
Antimony Plating 130°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-	
Arsenic Plating 110°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-	
Brass Plating																										
Regular Brass Bath 100°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-	
High Speed Brass Bath 110°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-	
Bronze Plating																										
Copper Cadmium Bronze Bath R.T.	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-	
Copper-Tin Bronze Bath 160°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-	
Copper-Zinc Bronze Bath 100°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-	
Cadmium Plating																										
Cyanide Bath 90°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-	
Fluoborate Bath 100°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-	
Chromium Plating																										
Chromic-Sulfuric Bath 130°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-	
Fluosilicate Bath 95°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A			A	-	-	
Fluoride Bath 130 °F	A	-	-		-	D	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-	
Black Chrome Bath 115°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-	
Barrel Chrome Bath 95°F	A	-	-		-	D	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-	

Tableau de compatibilité



Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Copper Plating (Cyanide)																									
Copper Strike Bath 120°F	-	-	-		-	-	A	-		-	A		-	-	A	-		-	-	A	-		-	-	-
Rochelle Salt Bath 150°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
High Speed Bath 180°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
Copper Plating (Acid)																									
Copper Sulfate Bath R.T.	A	-	-		-	D	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
Copper Fluoroborate Bath 120°F	A	-	-		-	D	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-
Copper (Misc.)																									
Copper Pyrophosphate 140°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
Copper (Electroless) 140°F	A	-	-		-	-	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
Gold Plating																									
Cyanide 150°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
Neutral 75°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
Acid 75°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
Indium Sulfamate Plating	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
Iron Plating																									
Ferrous Chloride Bath 190°F	C	-	-		-	D	A	-		-	A		-	-	A	-		C	-	A	-		C	-	-
Ferrous Sulfate Bath 150°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-
Ferrous Am. Sulfate Bath 150°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-
Sulfate-Chloride Bath 160°F	A	-	-		-	D	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003		
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel		
Fluoborate Bath 145°F	A	-	-		-	D	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
Sulfamate 140°F	A	-	-		-	D	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
Lead Fluoborate Plating	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-		
Nickel Plating																											
Watts Type 115-160°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
High Chloride 130-160°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
Fluoborate 100-170°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-		
Sulfamate 140°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
Electroless 200°F	D	-	-		-	-	A	-		-	A		-	-	A	-		D	-	A	-		D	-	-		
Rhodium Plating 120°F	A	-	-		-	D	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
Silver Plating 80-120°F	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-		
Tin-Fluoborate Plating 100°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-		
Tine-Lead Plating 100°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
Zinc Plating																											
Acid Chloride 140°F	A	-	-		-	D	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
Acid Sulfate Bath 150°F	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-		
Acid Fluoborate Bath R.T.	A	-	-		-	-	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
Alkaline Cyanide Bath R.T.	A	-	-		-	-	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-		
Potash	A	B	A		-	-	-	-		A	-		-	A	-	-		A	-	-	C		A	B	-		
Potassium Bicarbonate	A	B	A		A	-	A	A		A	A		A	A	A	A		A	A	A	A		A	B	D		

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Potassium Bromide	A	B	A		C	-	A	A		A	A		C	A	A	A		A	A	A	-		A	B	D
Potassium Carbonate	A	B	A		A	-	A	A		A	A		A	A	A	A		A	A	A	A		A	B	-
Potassium Chlorate	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A			A	B	-
Potassium Chloride	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	A		A	B	-
Potassium Chromate	-	B	-		A	B	-	-		-	-		A	-	-	-		-	-	-	D		-	B	-
Potassium Cyanide Solutions	A	B	A		A	B	A	A		A	A		A	A	A	A		A	A	A	D		A	B	-
Potassium Dichromate	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	D		A	B	-
Potassium Ferrocyanide	-	A	A		-	-	A	-		A	A		-	A	A	-		-	-	A	-		-	A	-
Potassium Hydroxide (50%)	A	B	B		A	B	A	D		B	A		A	B	A	D		A	D	A	C		A	B	C
Potassium Nitrate	A	B	A		C	B	A	A		A	A		C	A	A	A		A	A	A	-		A	B	-
Potassium Permanganate	B	B	A		A	B	A	A		A	A		A	A	A	A		B	A	A	A		B	B	-
Potassium Sulfate	A	B	A		A	B	A	A		A	A		A	A	A	A		A	A	A	A		A	B	-
Potassium Sulfide	-	-	A		-	-	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-
Propane (Liquified)1 2	D	-	A		-	-	A	-		A	A		-	A	A	-		D	-	A	-		D	-	-
Propylene Glycol	-	B	B		-	-	A	-		B	A		-	B	A	-		-	-	A	A		-	B	-
Pyridine	B	C	C		A	-	A	D		C	A		A	C	A	D		B	D	A	-		B	C	-
Pyrogallic Acid	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-
Rosins	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	-	-
Rum	A	-	A		-	-	-	-		A	-		-	A	-	-		A	-	-	A		A	-	-

Tableau de compatibilité



Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Rust Inhibitors	A	-	A		-	-	-	-		A	-		-	A	-	-		A	-	-	A		A	-	-
Salad Dressing	A	-	A		-	-	-	-		A	-		-	A	-	-		A	-	-	D		A	-	D
Sea Water	A	B	A		-	C	A	-		A	A		-	A	A	-		A	-	A	A		A	B	-
Shellac (Bleached)	A	-	A		-	-	A	-		A	A		-	A	A	-		A	-	A	-		A	-	-
Shellac (Orange)	A	-	A		-	-	A	-		A	A		-	A	A	-		A	-	A	-		A	-	C
Silicone	A	-	B		-	-	-	-		B	-		-	B	-	-		A	-	-	-		A	-	-
Silver Bromide	-	-	C		-	C	-	-		C	-		-	C	-	-		-	-	-	-		-	-	-
Silver Nitrate	A	B	A		-	B	A	A		A	A		-	A	A	A		A	A	A	A		A	B	D
Soap Solutions ¹	A	B	A		A	A	A	-		A	A		A	A	A	-		A	-	A	A		A	B	C
Soda Ash (See Sodium Carbonate)																									
Sodium Acetate	A	B	A		-	A	A	A		A	A		-	A	A	A		A	A	A	-		A	B	C
Sodium Aluminate	-	-	-		A	-	A	-		-	A		A	-	A	-		-	-	A	-		-	-	-
Sodium Bicarbonate	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	A		A	B	C
Sodium Bisulfate	A	B	A		A	-	A	A		A	A		A	A	A	A		A	A	A	A		A	B	D
Sodium Bisulfite	A	B	A		A	-	A	A		A	A		A	A	A	A		A	A	A	D		A	B	D
Sodium Borate	-	A	A		-	-	A	-		A	A		-	A	A	-		-	-	A	-		-	A	C
Sodium Carbonate	A	B	A		A	B	A	A		A	A		A	A	A	A		A	A	A	-		A	B	-
Sodium Chlorate	A	B	A		A	-	A	A		A	A		A	A	A	A		A	A	A	-		A	B	-
Sodium Chloride	A	B	A		A	C	A	A		A	A		A	A	A	A		A	A	A	A		A	B	-

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Sodium Chromate	A	-	A		A	A	A	-		A	A		A	A	A	-		A	-	A	D		A	-	-
Sodium Cyanide	A	B	A		A	-	A	A		A	A		A	A	A	A		A	A	A	A		A	B	-
Sodium Fluoride	-	C	C		-	-	A	-		C	A		-	C	A	-		-	-	A	-		-	C	D
Sodium Hydrosulfite	-	-	-		-	-	A	-		-	A		-	-	A	-		-	-	A	-		-	-	-
Sodium Hydroxide/Caustic Soda (20%)	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	C		A	B	-
Sodium Hydroxide/Caustic Soda (50%)	A	C	A		B	B	A	D		A	A		B	A	A	D		A	D	A	D		A	C	-
Sodium Hydroxide/Caustic Soda (80%)	A	C	A		B	D	A	-		A	A		B	A	A	-		A	-	A	D		A	C	C
Sodium Hypochlorite/Bleach3 (to 20%)	C	B	C		C	C	A	-		C	A		C	C	A	-		C	-	A	D		C	B	D
Sodium Hypochlorite/Bleach	C	-	-		C	D	A	A		-	A		C	-	A	A		C	A	A	-		C	-	D
Sodium Hyposulfate	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-
Sodium Metaphosphate2	D	-	-		-	A	A	-		-	A		-	-	A	-		D	-	A	A		D	-	-
Sodium Metasilicate	-	-	-		-	A	A	-		-	A		-	-	A	-		-	-	A			-	-	C
Sodium Nitrate	A	B	A		-	A	A	A		A	A		-	A	A	A		A	A	A	A		A	B	-
Sodium Perborate	A	-	-		-	C	A	-		-	A		-	-	A	-		A	-	A	A		A	-	-
Sodium Peroxide	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	A		-	-	D
Sodium Polyphosphate (Mono, Di, Tribasic)	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	A		-	-	-
Sodium Silicate	A	-	A		-	B	A	-		A	A		-	A	A	-		A	-	A	A		A	-	-
Sodium Sulfate	A	B	A		A	A	A	-		A	A		A	A	A	-		A	-	A	A		A	B	-

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Sodium Sulfide	A	B	A		A	B	A	-		A	A		A	A	A	-		A	-	A	D		A	B	-
Sodium Sulfite	-	A	C		-	C	A	-		C	A		-	C	A	-		-	-	A	A		-	A	-
Sodium Tetraborate	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Sodium Thiosulphate ("Hypo")	A	-	A		A	A	A	-		A	A		A	A	A	-		A	-	A	A		A	-	C
Sorghum	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	D		-	-	-
Soy Sauce	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	D		-	-	D
Stannic Chloride	A	B	D		-	D	A	A		D	A		-	D	A	A		A	A	A	-		A	B	D
Stannic Fluoborate	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	A		-	-	D
Stannous Chloride	-	A	D		-	C	A	-		D	A		-	D	A	-		-	-	A	-		-	A	D
Starch	-	B	A		-	A	A	-		A	A		-	A	A	-		-	-	A	A		-	B	C
Stearic Acid2	-	B	A		-	A	A	A		A	A		-	A	A	A		-	A	A	-		-	B	C
Stoddard Solvent	D	D	A		A	A	A	A		A	A		A	A	A	A		D	A	A	D		D	D	-
Styrene	-	-	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-
Sugar (Liquids)	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	-	-
Sulfate Liquors	A	-	C		-	C	-	-		C	-		-	C	-	-		A	-	-	-		A	-	-
Sulfur Chloride	D	A	D		-	D	A	-		D	A		-	D	A	-		D	-	A	-		D	A	-
Sulfur Dioxide2	D	C	A		A	A	A	B		A	A		A	A	A	B		D	B	A	A		D	C	-
Sulfur Dioxide (dry)	-	D	A		-	A	A	-		A	A		-	A	A	-		-	-	A	-		-	D	-
Sulfur Trioxide (dry)	-	-	A		-	C	A	-		A	A		-	A	A	-		-	-	A	-		-	-	-

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Sulfuric Acid (to 10%)	A	B	D		A	C	A	A		D	A		A	D	A	A		A	A	A	D		A	B	D
Sulfuric Acid (10%-75%) ²	A	C	D		B	D	A	A		D	A		B	D	A	A		A	A	A	D		A	C	D
Sulfuric Acid (75%-100%)	B	-	-		C	D	A	A		-	A		C	-	A	A		B	A	A	D		B	-	-
Sulfurous Acid	A	B	C		-	B	A	-		C	A		-	C	A	-		A	-	A	D		A	B	D
Sulfuryl Chloride	-	-	-		-	-	A	-		-	A		-	-	A	-		-	-	A	-		-	-	-
Syrup	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	-		A	-	-
Tallow	-	C	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	C	-
Tannic Acid	A	B	A		-	A	A	A		A	A		-	A	A	A		A	A	A	-		A	B	C
Tanning Liquors	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	C		A	-	-
Tartaric Acid	A	B	A		-	B	A	A		A	A		-	A	A	A		A	A	A	A		A	B	D
Tetrachlorethane	A	-	-		-	A	A	-		-	A		-	-	A	-		A	-	A	-		A	-	-
Tetrahydrofuran	C	D	A		A	A	A	D		A	A		A	A	A	D		C	D	A	-		C	D	D
Toluene, Toluol ³	D	D	A		A	A	A	A		A	A		A	A	A	A		D	A	A	A		D	D	-
Tomato Juice	A	-	A		A	A	A	-		A	A		A	A	A	-		A	-	A	-		A	-	C
Trichlorethane	-	-	C		-	A	A	-		C	A		-	C	A	-		-	-	A	-		-	-	C
Trichlorethylene ²	D	D	A		C	A	A	A		A	A		C	A	A	A		D	A	A	A		D	D	C
Trichloropropane	-	-	-		-	A	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-
Tricresylphosphate	-	-	-		-	A	A	-		-	A		-	-	A	-		-	-	A	-		-	-	-
Triethylamine	-	-	-		-	-	-	-		-	-		-	-	-	-		-	-	-	-		-	-	-

Tableau de compatibilité

PRESSOL

Fluids	13 003 001	13 003 001	13 003 001		13 003 002	13 003 002	13 003 002	13 003 002		13 005	13 005		13 064 001	13 064 001	13 064 001	13 064 001		13 064	13 064	13 064	13 064		13 003	13 003	13 003
	Polypropylene	Polyethylene	304 Stainless Steel		PPS	316 Stainless Steel	PTFE	PVDF		304 Stainless Steel	PTFE		PPS	304 Stainless Steel	PTFE	PVDF		Polypropylene	PVDF	PTFE	Phenolic		Polypropylene	Polyethylene	Steel
Turpentine3	B	D	A		A	A	A	A		A	A		A	A	A	A		B	A	A	-		B	D	-
Urine	A	B	A		-	A	-	-		A	-		-	A	-	-		A	-	-	A		A	B	-
Vegetable Juice	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	A		-	-	D
Vinegar	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	-		A	B	C
Varniah (Use Viton for Aromatic)	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	-		A	-	-
Water, Acid, Mine	A	-	A		B	A	-	-		A	-		B	A	-	-		A	-	-	-		A	-	C
Water, Distilled, Lab Grade	A	-	A		A	A	A	-		A	A		A	A	A	-		A	-	A	A		A	-	D
Water, Fresh	A	A	A		A	A	A	-		A	A		A	A	A	-		A	-	A	A		A	A	-
Water, Salt	A	-	A		A	A	-	-		A	-		A	A	-	-		A	-	-	A		A	-	D
Weed Killers	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Whey	-	-	A		-	A	-	-		A	-		-	A	-	-		-	-	-	-		-	-	-
Whiskey and Wines	A	B	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	B	D
White Liquor (Pulp Mill)	A	-	A		-	A	A	-		A	A		-	A	A	-		A	-	A	A		A	-	C
White Water (Paper Mill)	A	-	A		-	A	-	-		A	-		-	A	-	-		A	-	-	-		A	-	-
Xylene2	D	D	A		A	A	A	A		A	A		A	A	A	A		D	A	A	A		D	D	-
Zinc Chloride	A	B	D		A	B	A	A		D	A		A	D	A	A		A	A	A	A		A	B	D
Zinc Hydrosulphite	-	-	-		A	A	-	-		-	-		A	-	-	-		-	-	-	A		-	-	D
Zinc Sulfate	A	B	A		A	A	A	A		A	A		A	A	A	A		A	A	A	A		A	B	C